

# Fiber Glass-Reinforced, Mineral Surfaced Cap Sheet


#### Meets the requirements of ASTM D 3909

#### **Features and Components**

GlasKap is used as a cap sheet in a variety of built up roofing systems.

Asphalt Coated, Fiber Glass Reinforcement Mat: Low moisture, excellent dimensional stability and resistance to rot make it an ideal replacement for organic cap sheets.

Ceramic-Coated Granules: Provide protection to the underlying bitumen and membrane, and have a low maintenance cost compared to roofs that use coatings.



Waterproofing



System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Ply	BUR		APP		SBS			Ply		ГРО	PVC		EPDM		
-jāj	HA CA	CA	HW	HA	CA	HW	SA	gle	MF	FA	MF	FA	MF	FA	BA
Βſ	Compatible with the selected Multi-Ply systems above						Sin	یق Do not use with Single Ply systems							
Kev <sup>.</sup>	HA = Hot An	blied C	$\mathbf{A} = Cold An$	nlied H	W = Heat	t Weldahle	SA =	Self Adhere	M be	F = Mechani	cally Fastene	d <b>FA</b> =	Fully Adher	ed BA	= Ballasted

#### **Energy and the Environment**

Pre-Consumer Recycled Content	0%
Post-Consumer Recycled Content	0%

## **Peak Advantage® Guarantee Information**

Systems	Guarantee Term
Dependent on system	Up to 20 years

\*Contact JM Technical Services for specific system requirements or guarantee terms.

#### **Codes and Approvals**





- Classified by Underwriters Laboratories Inc. as a Type G-3 Coated Cap Sheet. See the UL® Roofing Materials and Systems Directory for acceptable Class A, B or C roof constructions employing GlasKap.
- FM Global<sup>®</sup> has approved the use of this product in numerous constructions.

#### Installation/Application



Hot Asphalt Cold Applied

- When installing GlasKap, it is important that the mopping asphalt be at the appropriate temperature: 20°F (11°C) above the asphalt's EVT is recommended.
- Refer to JM BUR application guides and detail drawings for instructions.

## **Packaging and Dimensions**

Roll Width	36" (914 mm)			
Roll Length	36' (10.97 m)			
Roll Coverage*	101 ft <sup>2</sup> (9.38 m <sup>2</sup> )			
Roll Weight	72 lb (32.6kg)			
Rolls per Pallet	30			
Pallets per Truck**	21			

\*Assumes 2" side lap and 4" end lap. \*\*Assumes 48' flatbed truck.

Refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the Web at www.jm.com/roofing.



# Meets the requirements of ASTM D 3909

# **Tested Physical Properties**

Phy	sical Properties	ASTM Test Method	Standard for ASTM D 3909 (Min)	GlasKap	
	Average Mass per Roll, Exclusive of Wrapping and Packaging Material <i>(min)</i> : No Selvage	D 228	≥ 69 lb	69 lb (31.3 kg)	
	Mass Per Unit Area of Mineral-surfaced Sheet (min)	D 228	$\geq$ 63.2 lb/100ft <sup>2</sup>	63.9 lb/100 ft <sup>2</sup>	
ss	Mass Per Unit Area of Desaturated Glass Felt (min)	D 228	$\geq$ 1.7 lb/100ft <sup>2</sup>	1.85 lb/100 ft² (90 g/m²)	
Mass	Mass Per Unit Area of Mineral Matter Passing a 0.132 in. (3.35 mm) (No. 6) Sieve and Retained on a 212 µm (No. 70) Sieve (min)	D 228	$\geq$ 24 lb/100ft <sup>2</sup>	24 lb/100 ft <sup>2</sup>	
	Mass of Mineral Matter Passing a 212 µm (No. 70) Sieve Based on Mass of Coating Asphalt and Mineral Matter Passing the 212 µm (No. 70) Sieve <i>(max)</i>	D 228	≤ 55%	55%	
Moisture	Moisture at Point of Manufacture (max)	D 95	1.0%	≤ 1.0 <i>%</i>	