

JM EPDM R 60 MIL - FIT (N

Polyester-Reinforced Ethylene Propylene Diene Monomer Membrane

Meets the requirements of ASTM D 4637, Type II

Features and Components

Membrane: Cured EPDM (ethylene propylene diene monomer) reinforced with a tough 1,000+ denier polyester mat. Excellent puncture and hail resistance.

Factory Inseam Tape: For superior quality assurance and labor savings compared to field fabricated seams. The factory inseam tape is designed with easy-release zip strip for application with Johns Manville 1" Polymer Batten Strip.

Fully Extruded: Produces fewer air voids, more uniform thickness and smoother sheets.

Vulcanization Process: Combines two layers of membrane to produce a fully cross-linked monolithic membrane.

Polvmer Formulation: Performs in extreme temperature climates and withstands differential movement (elongation).

UV-Stabilization Properties: Offers outstanding ozone and weather resistance delivering one of the longest service lives available.

Technical Expertise: Backed by 30+ years of EPDM experience and installations.





Single Ply

Color

Black

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

P	BUR		APP		SBS			
堇	HA	CA	CA	HW	HA	CA	HW	SA
Ę	Do not use with Multi-Ply systems							

Multi-F	HA C	A C/	A HW	НА	CA	HW	SA
Ē		Do	not use witi	h Multi-Ply	systems		
Kov.	HA - Hot	Annlied	CA - Cold	Annlied	HW – Ho	at Woldahl	Δ2 ما

SA = Self Adhered

MF = Mechanically Fastened

Compatible with the selected Single Ply systems above **AD** = Adhered

EPDM

BA = Ballasted

Energy and the Environment

Property	Value		
Reflectivity* (ASTM C 1549)	0.06		
Emissivity* (ASTM C 1371)	0.87		
Post-consumer Recycled Content	0%		
Pre-Consumer Recycled Content	0%		

^{*}Test methods for reflectivity and emissivity are LEED®- and CRRC®-approved.

Peak Advantage® Guarantee Information

Enhanced guarantees are now available on certain systems for wind and puncture. Consult your local sales representative for more information and for specific guarantee terms and costs

Product	Guarantee Term
JM EPDM R 60 mil - FIT (MF)	Up to 20 years

Codes and Approvals





Refer to the Safe Use Instructions and product label prior to using this product. The Safe Use Instructions are available by calling (800) 922-5922 or on the Web at www.jm.com/roofing.

Installation/Application



Refer to JM EPDM Application Guides and Detail Drawings for instructions.

Packaging and Dimensions

Roll Size*	Roll Coverage	Factory Inseam Tape Width	
10' x 100' (3.05 m x 30.48 m)	1000 ft ² (92.9 m ²)	6 " (152 mm)	
Membrane extruded in:	Milan, OH		

^{*}More roll sizes to be added. Please contact your local sales representative for current product offering.

Storage

Shelf Life	12 months from manufacture date		
Storage Conditions	The Inseam tape at the end of each roll is susceptible to damage. Store away from areas or materials where punctures or physical damage is likely to occur. Store indoors, out of direct sunlight, keep clean and dry prior to use. Do not stack rolls on top of one another for extended periods of time.		
Temperature Range	60°F – 80°F (15.6°C – 26.7°C)		

^{*}Note: Product is not installed with plates



JM EPDM R 60 MIL - FIT (MF)

Polyester-Reinforced Ethylene Propylene Diene Monomer Membrane

Meets the requirements of ASTM D 4637, Type II

Tested Physical Properties

Physi	cal Properties	ASTM Test Method	Standard for ASTM D 4637, Type II	JM EPDM R 60 mil - FIT System (MF)
	Breaking Strength (lbf)	D 751 A	>= 90	251
	Elongation at Fabric Break, Ultimate (%)	D 751 A	>= 15	MD 37, XMD 37*
Strength	Elongation, Ultimate (%)	D 412	> = 250	452
Stre	Tear Strength (lbf)	D 751 B	>= 10	110
	Dynamic Puncture Resistance, 10J, Type II	D 5635	pass	pass
	Static Puncture Resistance, 55.1 lbf, Type II	D 5602	pass	pass
	Overall Sheet Thickness (in.)	D 751	+/- 10%	pass
. <u>≩</u> .	Thickness Over Scrim, Weathering Side (in.)	D 7635	0.015	0.026
Longevity	Brittleness Point (°F)	D 2137	<=-49	pass
2	Ozone Resistance	D 1149	pass	pass
	Water Absorption (mass %)	D 471	<=8	0.3
_ e e	Heat Aged 670 hrs @ 240°F	D 573		
Heat Aged Performance	Breaking Strength (lbf)	D 751	>= 80	232
leat erfor	Elongation, Ultimate (%)	D 412	> = 200	270
	Linear Dimensional Change (%)	D 1204	<±1	0.06
Weathering Performance	Weathering Resistance, 5040 KJ/(m2-nm) @ 340 nm	D 4637 / G 151 / G 155		
Weat	Visual Inspection	_	pass	pass

Physical Properties – Factory Inseam Tape

Physical Property	JM EPDM R 60 mil - FIT System (MF)		
Base	Rubber/Butyl polymer		
Color	Black		
Solvents	Residual Solvent Present		
Percent Solids	100%		
Cure State	Cured		
Thickness	25 mils (Nominal)		
Width	6" (152 mm)		
Release Liner	Polyester		